



10/525095
PCT/GB&W/03/000000



INVESTOR IN PEOPLE

PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

REC'D 10 OCT 2003

WIPO

PCT

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

Andrew Gersey

Dated

18 September 2003

Patents Form 1/77

Patents Act 1977
(Rule 16)

19 AUG 2002

RECEIVED BY FAX

The
Patent
Office19AUG02 E742069-1 D02973
P01/7700 0.00-0219272.2**Request for grant of a patent***(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)*

The Patent Office

Cardiff Road
Newport
South Wales
NP9 1RH

1. Your reference

P071963GB

2. Patent application number

(The Patent Office will fill in this part)

0219272.2

19 AUG 2002

3. Full name, address and postcode of the or of each applicant *(underline all surnames)*Uponor Innovation AB
Industrivägen
SE-51381 Fristad
SWEDENPatents ADP number *(if you know it)*

If the applicant is a corporate body, give the country/state of its incorporation

SWEDEN

4. Title of the invention

PLASTICS PIPE

5. Name of your agent *(if you have one)*

Harrison Goddard Foote

*"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)*Fountain Precinct
Leopold Street
Sheffield, S1 2QD
UNITED KINGDOMPatents ADP number *(if you know it)*

7914237001

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and *(if you know it)* the or each application number

Country

Priority application number
*(if you know it)*Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
*(day / month / year)*8. Is a statement of inventorship and of right to grant of a patent required in support of this request? *(Answer 'Yes' if**a) any applicant named in part 3 is not an inventor, or**b) there is an inventor who is not named as an applicant, or**c) any named applicant is a corporate body.**See note (d))*

Yes

Patents Form 1/77

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description

19

Claim(s)

5

Abstract

1

Drawing(s)

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (*Patents Form 7/77*)Request for preliminary examination and search (*Patents Form 9/77*)Request for substantive examination (*Patents Form 10/77*)Any other documents
(please specify)

11.

I/We request the grant of a patent on the basis of this application.

Signature

Date

19/08/02

12. Name and daytime telephone number of person to contact in the United Kingdom

Robert L Hall

0114 274 3704

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.


Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500506.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

Patents Form 1/77

Cut through the skin along mark at TDC & prise edge of skin from pipe, peel skin off to 30 - 40mm length, feed peeled skin through the jig as shown & clamp in upper jaws.

Mount the test piece in the jig as shown in Figure:



The skin is then peeled from the pipe at a separation rate of 100mm/min and a trace recorded of load versus time.

The average value of the load required to peel the skin sample is calculated (Newtons), and divided by the true width of the peel sample to obtain the test result (Newtons/millimetre).

The average of the 10 peak load values recorded is calculated (Newtons), and divided by the true width of the peel sample to obtain the test result (Newtons/millimetre).

5 The reader's attention is directed to all papers and documents which are filed concurrently with or previous to this specification in connection with this application and which are open to public inspection with this specification, and the contents of all such papers and documents are incorporated herein by reference.

10 All of the features disclosed in this specification (including any accompanying claims, abstract and drawings), and/or all of the steps of any method or process so disclosed, may be combined in any combination, except combinations where at least some of such features
15 and/or steps are mutually exclusive.

Each feature disclosed in this specification (including any accompanying claims, abstract and drawings), may be replaced by alternative features
20 serving the same, equivalent, or similar purpose, unless expressly stated otherwise. Thus, unless expressly stated otherwise, each feature disclosed is one example only of a generic series of equivalent or similar features.

25

The invention is not restricted to the details of any foregoing embodiments. The invention extends to any novel one, or any novel combination, of the features disclosed in this specification (including any
30 accompanying claims, abstract and drawings), or to any novel one, or any novel combination, of the steps of any method or process so disclosed.

CLAIMS

1. A plastics pipe which comprises an inner core and an outer removable skin layer bonded thereto,
- 5 the outer removable skin layer comprising a polymeric material, chosen for its physical and mechanical properties, and an adhesion-modifying additive,
- 10 the adhesion-modifying additive being present in the skin layer in an amount such that the adhesion of the skin layer to the inner core is sufficient to prevent substantial undesired relative movement between the skin layer and the core during installation, but insufficient
- 15 to prevent the outer skin layer from being cleanly removed by peeling, at least at the ends of the pipe, and insufficient to cause a substantial reduction in the impact strength of the inner core.
- 20 2. A plastics pipe according to claim 1, wherein the strength of the adhesive bond between the skin layer and the inner core is from 0.2 N/mm to 2.0 N/mm, when measured by a rolling drum peel test as described in Appendix 1.
- 25 3. A plastics pipe according to claim 1 or 2, wherein the strength of the adhesive bond between the skin layer and the inner core is from 0.3 N/mm to 1.5 N/mm, when measured by a rolling drum peel test as described in Appendix 1.
- 30 4. A plastics pipe according to any one of the preceding claims, in which the strength of the adhesive bond between the skin layer and the inner core is such that the impact strength of the
- 35

composite pipe is at least 50%, preferably 75%, of the impact strength of the inner core without the skin layer.

5

5. A plastics pipe according to any one of the preceding claims, in which the inner core comprises polyethylene.

10

6. A plastics pipe according to any one of the preceding claims, wherein the skin layer comprises a propylene homo-or co-polymer, a propylene block co-polymer, or a propylene random copolymer.

15

7. A plastics pipe according to claim 6, wherein the skin layer comprises a propylene block co-polymer.

20

8. A plastics pipe according to any one of the preceding claims, in which the inner core comprises polyethylene and the skin layer comprises a propylene co-polymer and wherein the impact strength of the pipe is greater than 300 joules, when measured using the method of EN1411:1996 at a temperature of -10°C using a 90mm tup for impacting the pipe.

25

9. A plastics pipe according to any one of the preceding claims, wherein the skin layer comprises an adherent polymeric material and an appropriate amount of an adhesion-reducing additive.

30

10. A plastics pipe according to claim 9, wherein the adhesion-reducing additive in the skin layer is present in an amount of from 0.5% to 10% by weight.

35

11. A plastics pipe according to claim 9 or 10, wherein the adhesion reducing additive is an ester of a polyhydric alcohol.
- 5 12. A plastics pipe according to claim 11, wherein the polyhydric alcohol is glycerol.
13. A plastics pipe according to claim 11 or 12, wherein the ester is a fatty acid ester.
- 10 14. A plastics pipe according to any one of the preceding claims, which comprises an inner core of polyethylene and a skin layer of a propylene block copolymer comprising about 3% of a glycerol ester.
- 15 15. A plastics pipe according to any one of claims 1 to 10, wherein the adhesion-reducing additive is a fatty acid amide.
- 20 16. A plastics pipe according to any one of the preceding claims, wherein the skin layer has a thickness within the range of from 0.2 mm to 2.0 mm.
- 25 17. A plastics pipe according to any one of the preceding claims, wherein the ratio of the external diameter of the pipe to the thickness of the skin layer is from 100 to 800.
- 30 18. A plastics pipe according to any one of the preceding claims, wherein the strength (in N per mm of width) of the skin layer exceeds the peel strength (in N per mm width) of the adhesive bond between the outer removable skin layer and the
- 35 inner core.

19. A plastics pipe substantially as hereinbefore described.
- 5 20. A method for the production of a plastics pipe comprising an inner core and an outer removable skin layer bonded thereto, the outer removable skin layer comprising a polymeric material chosen for its physical and mechanical properties, and an effective amount of an adhesion-modifying additive, which method comprises co-extruding molten polymeric materials forming the inner core and the outer removable skin layer from one or more extruder dies, bringing the molten polymeric materials together and allowing them to cool, such that, on cooling, the adhesion of the skin layer to the inner core is sufficient to prevent substantial undesired relative movement between the skin layer and the core during installation of the pipe, but insufficient to prevent the skin layer from being cleanly removed by peeling, at least at the ends of the pipe, and insufficient to cause a substantial reduction in the impact strength of the inner core.
- 10 21. A method according to claim 20, wherein the polymeric materials of the inner core and the outer removable skin layer are extruded simultaneously and brought together whilst still molten.
- 15 22. A method according to claim 20 or 21, substantially as described in the Example.
- 20 23. A method of making a joint to a plastics pipe according to any one of claims 1 to 19, or of joining two such plastics pipes, which comprises
- 25 30 35

24

5

peeling the skin layer from the region or regions of the pipe to be joined, to expose a clean surface suitable for electrofusion jointing, installing an electrofusion fitting over the clean surface or surfaces of the pipe or pipes and activating the electrofusion fitting to fuse the region or regions of the pipe or pipes thereto.

10

Abstract

A plastics pipe which comprises an inner core and an
5 outer removable skin layer bonded thereto,
the outer removable skin layer comprising at least two
layers of compatible polymeric materials, a first outer
protective layer chosen for its physical and mechanical
10 properties, and a second inner bonding layer which
adheres to the inner core, the adhesion of the bonding
layer to the inner core being sufficient to prevent
substantial undesired relative movement between the skin
layer and the core during installation, but insufficient
15 to prevent the outer skin layer from being cleanly
removed by peeling, at least at the ends of the pipe, and
insufficient to cause a substantial reduction in the
impact strength of the inner core.

20

25

PLASTICS PIPE

This invention relates to plastic pipes and more particularly to a novel composite plastics pipe, a method
5 for its manufacture, and a method for making joints in such a pipe.

In the handling, installation and connection of plastics pipes, the pipe surface is easily damaged. In
10 "no-dig" plastics pipe installation techniques, for example, a tunnel is bored in the ground for the pipe and the pipe is then pushed or pulled through the tunnel into an excavated hole where the next pipe joint is to be
15 made. Installation techniques such as pipe-bursting and slip lining can also place extreme stress on the pipe surface.

Other modern pipe laying methods can also subject the pipe to substantial bending and tensile forces, both
20 of which can result in a deterioration of the mechanical strength of the pipe. In addition, the useful life of the pipe may be reduced by diffusible materials in the ground, or by environment conditions, for example, exposure to direct sunlight for long periods.

25 Of greatest concern, is that modern pipe laying methods can result in the pipe becoming scratched and dirty. This is disadvantageous firstly as the pipe material may be notch sensitive, in which case any
30 scratches may cause greater damage to occur in the pipe during subsequent handling or use. Secondly, dirt and/or oxidation on the pipe surface may prevent successful welding. The main reason for failure of joints using an electrofusion fitting is that the surface of the pipe is
35 dirty or has become oxidised. For this reason, until

recently, the pipe ends always have had to be cleaned and scraped before jointing, for example, with a hand or mechanical scraper. In practice, the cleaning and scraping is often uneven (the underside of the pipe in particular may be treated less carefully), and the quality of the end result depends upon the professional skill of the installer.

In recent years there have been proposals to provide the pipe with a non-adherent skin layer which can be removed in order to permit jointing. Composite pipe constructions of this type are described, for example, in JP3-24392, EP0474583, EP0604907, GB2323556, GB2300456, and WO93/00212. The entire disclosures of all these patents are incorporated herein by reference for all purposes.

All of these prior art pipe constructions suffer from the disadvantage that modern pipe laying techniques tend to cause wrinkling, rucking, or at least undesired movement of the non-adherent skin layer relative to the core when the pipe is pushed through the ground. These proposals have therefore not proved commercially acceptable.

More traditional proposals, wherein a protective skin layer is provided which is strongly adherent to the pipe, do not, of course, overcome the problem of dirt and oxidation on the outer surface, since such skin layers are very difficult to remove without elaborate equipment. The presence of a tightly adherent skin layer can also dramatically lower the impact strength of the plastics pipe.

The first appreciation that the above problems could

be solved by using a protective skin layer which is only lightly adherent to the core pipe occurs in GB2297137 and GB2297138, the entire disclosures of which are incorporated herein by reference for all purposes.

5

In GB2297138, for example, there is provided a plastics pipe which comprises an inner core and an outer protective layer bonded thereto, in which the dimensions of the pipe and the protective layer are such that the
10 ratio of the external diameter of the pipe to the thickness of the protective layer is at least 70, preferably at least a 100, and the cohesive strength of the outer protective layer, excluding any lines of
15 weakness, at least at the ends of the pipe, is greater than the strength of the adhesive bond between the outer protective layer and the inner core. According to this specification, by a correct choice of the material of the skin layer and the extrusion conditions, it is possible
20 to provide a level of adhesion which still permits clean removal of the skin layer by peeling, whilst preventing rucking or wrinkling of the skin layer during installation and without substantially adversely affecting the mechanical properties of the pipe.

25

The composite pipe of UK patents GB2297137 and GB2297138 has been commercially extremely successful, but it has been found that under specific conditions of temperature and loading it is difficult to provide a skin layer which has both the required toughness and limited
30 adhesion to the core pipe. Quality control of the base polymer material of the skin layer, and control of the extrusion conditions during manufacture, need to be rigorously maintained if undesirable quantities of scrap are to be avoided. This substantially increases both raw
35 material and manufacturing costs.

A novel composite plastics pipe has now been developed which has the advantages of a plastics pipe with a removable outer protective layer, but which gives
5 improved flexibility in choice of materials and manufacturing conditions without substantially adversely affecting the mechanical properties of the pipe.

In a first aspect, the invention provides a plastics
10 pipe which comprises an inner core and an outer removable skin layer bonded thereto,

the outer removable skin layer comprising a polymeric material, chosen for its physical and mechanical properties, and an adhesion-modifying
15 additive,

the adhesion-modifying additive being present in the skin layer in an amount such that the adhesion of the skin layer to the inner core is sufficient to prevent
20 substantial undesired relative movement between the skin layer and the core during installation, but insufficient to prevent the outer skin layer from being cleanly removed by peeling, at least at the ends of the pipe, and insufficient to cause a substantial reduction in the
25 impact strength of the inner core.

In a further aspect, the invention provides a method for the production of a plastics pipe comprising an inner core and an outer removable skin layer bonded thereto,
30 the outer removable skin layer comprising a polymeric material chosen for its physical and mechanical properties, and an effective amount of an adhesion-modifying additive, which method comprises co-extruding molten polymeric materials forming the inner core and the
35 outer removable skin layer from one or more extruder

of the material of the skin layer no longer have to be a compromise between conflicting requirements.

5 The strength of the adhesive bond between the skin
layer and the inner core is preferably at least 0.1 N/mm,
more preferably at least 0.2 N/mm, when measured by a
rolling drum peel test as described in Appendix 1. The
adhesive bond between the skin layer and the inner core
is preferably less than 2.0 N/mm, more preferably less
10 than 1.5 N/mm. Very good results have been achieved
using an adhesion between the skin layer and the inner
core within the range of from 0.3 to 1.5 N/mm, when
measured by the above-mentioned rolling drum peel test.
Without wishing to be bound to any particular theory, it
15 is believed that the adhesion between the high molecular
weight polymers of the inner bonding layer and the core
is as a result of Van der Waals and/or diffusive bonding,
or similar forces.

20 It is likely that any adhesion between the skin
layer and the inner core will have some effect upon the
impact strength of the plastics pipe, and it is
presumably for this reason that prior art proposals
(other than GB2297137 and GB2297138) have always sought
25 to avoid adhesion between the skin layer and the core.
Nevertheless, it has been found that the combination of
the tough skin layer and the light bonding used in the
present invention can still produce a plastics pipe
having sufficient impact strength to meet the
30 requirements of all available standards. Moreover
improved impact strength over the products of GB2297137
and GB2297138 can also be obtained. Preferably the
strength of the adhesive bond between the skin layer and
the inner core is such that the impact strength of the
35 composite plastics pipe is at least 50%, preferably at

least 75%, more preferably at least 90% of the impact strength of the inner core without the skin layer.

5 The inner core and the skin layer of the composite plastics pipe of the present invention can comprise any suitable thermoplastic polymeric materials, consistent with the maintenance of the required properties. Suitable polymeric materials include, for example, olefinically-unsaturated polymers and co-polymers, for example, polyolefins such as polyethylene, polypropylene, 10 polybutene and polybutylene; ethylene and propylene co-polymers, for example, ethylene-vinyl acetate polymers, and propylene-vinyl acetate polymers; halogenated-vinyl polymers such as vinyl chloride polymers and co-polymers; 15 polyamides, for example, nylon 6, nylon 11 and nylon 66; polycarbonates; ABS polymers and ionomer polymers such as Surlyn (RTM).

20 The inner core of the pipe comprises a polymeric material chosen to be compatible with the particular application, and in particular with the fluid material to be conveyed by the pipe. For many applications polyethylene is the preferred material for the inner core. The grade of polyethylene chosen, that is to say, 25 high density, medium density, low density, or linear low density, will depend upon the particular application. Suitable grades of polyethylene for pressure pipe applications, preferably meet the requirements of at least one of prEN 12201-1 (except clause 4.2.1 and the 30 associated pigment or carbon black requirements if an unpigmented material is used), prEN12201-2 (except clause 5.2 and the associated pigment or carbon black requirements if an unpigmented material is used), prEN1555-1 (except clause 4.2.2 and the associated 35 pigment or carbon black requirements if an unpigmented

material is used) and prEN1555-2 (except clause 5.2 and the associated pigment or carbon black requirements if an unpigmented material is used).

- 5 Any suitable equivalent grade of polyethylene may, of course, also be used.

10 The skin layer is formed from a polymeric material or a blend of polymeric materials having good mechanical and physical properties, especially toughness and low temperature impact strength. Preferred polymeric materials for the skin layer comprise propylene homo- and co-polymers, propylene block co-polymers, and propylene
15 random co-polymers. Preferably the skin layer has a notched Charpy impact strength of at least 1 kJ/m², more preferably at least 2 kJ/m² and most preferably at least 4 kJ/m², when measured using the method of ISO 179/16A at a temperature of -20°C.

20

Under typical co-extrusion conditions, many polymer material combinations tend to adhere strongly together, and this is generally true for many grades of polyethylene and propylene polymers. In this
25 specification, polymeric materials of the skin layer are termed "adherent polymeric materials", if, but for the presence of the adhesion reducing additive, they would adhere to the core pipe to an extent such that the outer skin layer cannot be peeled from the core pipe, or such
30 that the impact strength of the composite plastics pipe is substantially reduced, or both, when the core pipe and the skin layer are extruded under typical extrusion conditions. In such cases the skin layer will need to comprise an appropriate amount of an adhesion-reducing
35 additive.

The quantity of adhesion-reducing additive in the polymeric material of the skin layer is preferably such that the adhesion to the inner core is below 2.0N/mm and preferably below 1.0N/mm when measured using a rolling drum peel test as described in Appendix 1. The actual quantity of adhesion-reducing additive in the skin layer depends on the additive used, but in general is within the range of from 0.0001% to 15% by weight, more preferably from 0.5% to 10% by weight and most preferably from 1.0% to 8% by weight.

The adhesion-reducing additive is desirably one that has little or no effect on the mechanical and physical properties of the polymeric material of the skin layer. Preferred adhesion-reducing additives include esters, and, for example, one class of preferred esters includes esters of polyhydric alcohols such as ethane-1,2-diol, 2,2-dimethyl-1,3-propanediol (neopentyl glycol), 2-methyl-2-propyl-1,3-propanediol, 2-butyl-2-ethyl-1,3-propanediol, 2-butyl-2-methyl-1,3-propanediol, 1,3-propanediol, 2-methyl-1,3-propanediol, 1,2-pentanediol, 1,6-hexanediol, 3-hexyne-2,5-diol, 2,5-dimethyl-3-hexyne-2,5-diol, 1,10-decanediol, 2,2-bis(4-hydroxycyclohexyl)propane, 1,4-bis(hydroxymethyl)cyclohexane, 2,2,4-trimethyl-1,3-pentanediol, glycerol (propane-1,2,3-triol), trimethylolethane, trimethylolpropane, ditrimethylolpropane, pentaerythritol, dipentaerythritol, tripentaerythritol, sorbitol and mannitol.

Another class of preferred esters includes esters of fatty acids such as decanoic acid, docosanoic acid, dodecanoic acid (lauric acid), hexadecanoic acid (palmitic acid), octadecanoic acid, octanoic acid

(caprylic acid), oleic acid, linoleic acid, linolenic acid, octadecanoic acid (stearic acid), behenic acid, erucic acid, myristic acid, nonanoic acid, and ricinoleic acid.

5

Examples of preferred esters of polyhydric alcohols include glycerol esters with erucic acid, stearic acid, lauric acid, linoleic acid, myristic acid, oleic acid, palmitic acid, ricinoleic acid and behenic acid.

10

Examples of preferred esters of fatty acids include hexadecanoic acid, 2, 3,-bis [(trimethylsilyl)oxy] propyl ester and octadecanoic acid, 2, 3,-bis [(trimethylsilyl)oxy] propyl ester.

15

Another class of preferred esters includes cyclic esters of hydroxycarboxylic acids, for example, γ -butyrolactone, which is the cyclic ester of 4-hydroxybutyric acid.

20

Yet another class of preferred adhesion reducing additives includes acid anhydrides, for example, propanoic acid 2-methyl anhydride.

25

Still further classes of adhesion-reducing additives that can be used include fatty acid amides, for example oleamide, stearamide, erucamide and behenamide, and ethoxylated amines and esters.

30

Mixtures of any of the abovementioned adhesion-reducing additives may be used where compatible in any suitable combinations, proportions and amounts.

35

A particularly preferred plastics pipe according to the present invention comprises an inner core of

polyethylene and a skin layer of a propylene block copolymer comprising about 3% of a glycerol ester as an adhesion-reducing additive.

5 Preferably the impact strength of a 90 mm outside diameter plastics pipe having a polyethylene inner core and a polypropylene skin layer with an SDR of 17.0 is greater than 300 joules when measured using the method of EN1411:1996 at a temperature of -10°C using a 90mm
10 diameter tup for impacting the pipe.

The adhesion-modifying additive is preferably added to the polymeric material of the skin layer as a masterbatch. The masterbatch preferably comprises from
15 1% to 50% by weight of the adhesion-modifying additive, more preferably from 2% to 30% by weight.

In general, the use of processing aids, including stearates, such as calcium stearate, has been found to be
20 ineffective in reducing adhesion and should be avoided.

While the invention has been found to be particularly applicable to combinations of adherent polymeric materials and adhesion-reducing additives, in
25 principle it could also be applied to no-adherent polymeric materials, whereupon the adhesion-modifying additive would need to be an adhesion-promoting additive.

An advantage of the plastics pipes of the present
30 invention is that the normal UV stabiliser and colorant package need not be included in the plastics material of the inner core, provided that sufficient quantities of these materials are included in the skin layer. This enables the inner core to comprise a natural polymeric
35 material, free or substantially free from additives which

add to the cost of the core material and which, in certain circumstances, may impair the mechanical or physical properties of the core material. Alternatively, stabilisers can be included in the core material, but the outer protective skin layer can be coloured to indicate the underlying grade of pipe and/or the fluid being transported by the pipe.

Suitable stabiliser or ultra-violet blocking additives for the outer protective skin include, for example, titanium dioxide, carbon black, and other fillers. Whilst carbon black is an excellent UV stabiliser and reinforcing filler, buried pipes are frequently colour coded and its use in the outer protective layer is therefore not possible for many applications. Titanium dioxide is, therefore, the preferred filler and UV stabiliser since this is also compatible with many colorant packages. Other filler materials, such as chalk and talc, may also be used. The preferred filler particle size is dependent on the filler being used, but for titanium dioxide, for example, the average particle size range is preferable from 0.003 to 0.025 microns.

The skin layer and the inner core can, of course, each comprise more than one layer of polymeric material, although in practice this is not usually necessary.

The relative thickness of the skin layer and the dimensions of the pipe have also been found to affect the impact resistance of the pipe. This is discussed in GB 2297138. Preferably the skin layer has a thickness of greater than 0.1 mm, more preferably greater than 0.2 mm, and most preferably within the range of from about 0.3 mm to 2.0 mm.

- The dimensions of the pipe and the protective layer are preferably such that the ratio of the external diameter of the pipe to the thickness of the skin layer is at least 70, more preferably at least 100, most preferably in the range 100 to 800. From this it can be seen that it is possible to use a thicker skin layer on a pipe of greater diameter.
- When stripping the skin layer from the pipe, it is important that no residue or holidays should be left on the pipe surface that could interfere with the electrofusion jointing process. Thus conventional adhesives and skin layers that are prone to tearing or fragmentation should be avoided. In general the force required to rupture the skin layer should be greater than the force required to peel the skin layer from the inner core.
- By "a clean surface" in this specification is meant a pipe surface that can be subjected to electrofusion jointing without further preparation or treatment. Such surfaces should give rise to a quality of electrofusion joint that meets the requirements of one or more of pr EN12201 part 3, pr EN1555 part 3 and WIS 04-32-14.
- The composite plastics pipe of the present invention is preferably produced by co-extrusion, wherein the polymeric materials are brought together in the pressure area of the die and exit as a single extrudate. For example, the die may be connected to one, two, or more extruders and fed with separate streams of molten material. Alternatively, the die may be provided with concentric die outlets fed with separate streams of molten polymeric materials which are to form the inner

core and the skin layer. In this case, the extrudates, on leaving the extruder die outlets, can be brought into contact with each other whilst still molten, preferably in a sizing die which simultaneously adjusts the outer diameter of the pipe.

In a further alternative, the inner core extrudate may be passed through a sizing die before applying the skin layer. In this case it may be necessary to re-heat or flame-brush the surface of the inner core extrudate to create a surface ready to receive the skin layer. Because of the difficulty of maintaining a consistent adhesion between the inner core and the skin layer, and of keeping the core surface clean (prior to coating with the skin), this method is not presently preferred.

The method of the invention is illustrated by the following Example:

EXAMPLE

A polyethylene core pipe of nominal outer diameter 90mm was co-extruded with a propylene random copolymer skin layer. The experiment was repeated replacing the propylene random copolymer with (I) a propylene block copolymer and (II) with a blend of the copolymers, in each case with the addition of 15% by weight of a masterbatch comprising 20% of a glycerol ester.

Skin adhesion was measured using a rolling drum peel test as described in Appendix 1.

The skin layers of all of the resultant pipes could be peeled readily using a simple hand tool, exposing a clean surface of the core pipe. Electrofusion jointing tests gave very good results in conformance with prEN12201 part

3, prEN1555 part 3 and WIS 04-32-14. In a comparison test, a pipe was extruded with a propylene block copolymer skin layer without the glycerol ester. The skin layer firmly adhered to the core pipe and could not be removed from the pipe by peeling.

The impact strength of the pipes was measured at -10°C , with and without the skin layer, using the method of EN 1411:1996. In further experiments the pipes were notched at 90° to the point of impact prior to testing to simulate service conditions. The results are given in Table 1.

TABLE 1

PIPE			
\emptyset (MM) -SDR	90-17	90-17	90-17
Core resin	Polyethylene	Polyethylene	Polyethylene
SKIN			
Propylene random copolymer	100%	60%	-
Propylene block copolymer	-	25%	85%
Masterbatch	-	15% glycerol ester	15% glycerol ester
Thickness (mm)	0.5-1.0	0.79	0.67
SKIN ADHESION			
Min (N/mm)	0.3	0.79	1.08
Mean (N/mm)	-	1.38	1.55
Max (N/mm)	0.8	1.88	1.96
IMPACT at -10°C			
Un-Notched	103-324	<400	>588

(J)			
No skin, un-notched (J)	487-588		
Notched to 0.2mm depth (J)	103	188*	333*
No Skin, notched to 0.2mm depth (J)	387		

*Passed if the skin breaks but the core remains intact.

5 The results show that by using an adhesion-reducing additive to reduce the bond strength of a propylene block copolymer skin layer to a polyethylene core, the impact strength of the pipe can be substantially increased when compared to a similar pipe having a propylene random copolymer skin layer, whilst the peelability of the pipe

10 is retained.


APPENDIX 1**DETERMINATION OF THE ADHESION STRENGTH OF PIPE SKIN - CORE PEEL****5 Apparatus**

A tensile testing machine accurate to grade A of BS5214 : Part 1: 1975 or grade 1 of BS1610 : Part 1 : 1985, for example, a Lloyds tensile test machine, using a 100N load cell.

Test Specimens

Two test pieces are cut one from each end of the sample pipe, 25mm +/- 2mm wide, the two sample rings of pipe are trimmed around the circumference to remove the jagged edge. The pipe is marked along top dead centre (TDC) of the extrusion line (if known).

20 The two ring specimens are marked with an indelible marker at quarterly points around the circumference beginning at TDC (if known). (AS DRAWING)

**Procedure**